

LSZH 090 NATURAL

LOW SMOKE ZERO HALOGEN (LSZH / HFFR) INSULATION / SHEATHING COMPOUND

Description

LSZH 090 Natural is a Low Smoke Zero Halogen (LSZH / HFFR / ZHFR) thermoplastic, Flame Retardant & UV Stabilized Compound for Insulation & Sheathing / Jacketing of various types of cables like Power Cables, Optic fibre & Communication Cables, & Data Cables.

Processing

LSZH 090 Natural is a polyolefin based compound consisting of Polyolefin, Flame Retardants, Lubricants and additives. It exhibits good processing features and excellent Physical and Mechanical properties.

Specifications

LSZH 090 Natural compound meets the following specifications:

VDE 0207 PART 24 HM2 & HM 4 ICE 60332-1 / IEC 332-2-3- Category 'C'

IEC 60331 / IEC 60332/ BS 7655/ LTS 1, 3 & 4/ EN: 50363: 2005 / Type TI 6 & TI 7, IEC 60092 – SHF - 1

Salient Features

Good flow properties resulting in good extrusion & low amperage on the machine

- Good thermal and mechanical properties
- Good crack resistance properties
- Good flame retardant and low smoke properties

Technical Specifications Sheet

Properties	Test Method	Unit	Typical Value
a) Physical			
Density	ASTM D 792	gm/cc	1.48 +/- 0.02
MFI (21.6 kg @160°C)	ASTM D 1238	g/10 min	>2
b) Mechanical			
Hardness	ASTM D 2240	Shore D	48 +/- 2
Tensile Strength (250mm/min)	ASTM D 638	Mpa	Min 11
Elongation at Break (250mm/min)	ASTM D 638	%	>200
Variation in Tensile Properties After Heat Ageing (10 days at 100°C)			
• Tensile Strength	ASTM D 638	%	±20
• Elongation	ASTM D 638	%	±20
c) Thermal			
Limiting Oxygen Index	ASTM D 2863	%	Min 38
Temperature Index	ASTM D 2863	°C	Min 280
Test on Gases Evolved During Combustion			
• pH	IEC 60754-2		>4.3
• Conductivity	IEC 60754-2	µs/mm	<10
Smoke Density Rating	ASTM D 2843	%	<20

Processing Parameters

LSZH range of compounds is designed to perform on extruder with Low compression ratio screws meant for PE extrusion. However it can also be used on PVC extruder with limitation on output. The recommended temperature for extruding LSZH compound is in the range of 130°C to 150°C for barrel and 150°C for cross head and 165°C for die. Extra caution must be exerted to see that the processing temperature does not exceed 170°C which will result in degradation material. Pre-drying of the compound is recommended at 70°C for 2 hours to obtain smooth processing of the cable and attaining good surface finish on the cable.

Color Options

It is recommended to use RoHS compliant masterbatch for attaining the desired colour for the cables which conforms to RAL colour standards. We can also supply mass coloured compound as per the RAL Shade (Natural/Black). We recommend to use Black compounded product for demanding outdoor application.

Packaging, Storage & Transport

Package	Net Weight 25 kgs	PP Laminated Bags 500/1200 kgs - PP based Jumbo Bags
Transport	Requirement	Keep away from the sunshine, rain & soaking during transport, as well as handle gently while carrying.
Storage	Environment	Clean, dry and ventilated ware house

Technical Assistance

Our technical team will be available for assistance on request.

RoHS Compliance

LSZH 090 Natural Compound is RoHS Compliant.

Disclaimer

Revision 0: Nov 2022

The above mentioned recommendations are derived after various trials and checks conducted under different conditions. It is advised that the above stated information must be used as guidelines only. We suggest that the customer conducts their own trials and arrive at the optimum processing parameters which are best suited for their equipment and processing conditions. Sankhla does not take any responsibility for any sort of loss arising due to improper handling or usage of materials supplied.

Sankhla Vinyl Pvt. Ltd.

#75/2, 2nd Floor, Chaitra Court, Above Giria's Electronics Showroom,
Vani Vilas Road, Basavanagudi, Bengaluru 560 004, India
Mob: +91-99809 61025 | Email: cmho@sankhlapolymers.com